

# RUBBER SHEETING OIL RESISTANT 7645 — NBR-SBR



65 +/- 5	Sh A	3	MPa	1,65	g/cm <sup>3</sup>	200	%	-25 - +80	°C	1-15	mm	INTERIOR
HARDNESS		TENSILE STRENGTH		DENSITY		ELONGATION		TEMPERATURE RANGE		THICKNESS		ENVIRONMENT

Sealing plate designed for the environment in which it comes into contact with mineral oils (NBR45 series) and gasoline, resp. isooctanes (higher NBR72 series). Made from a synthetic mixture of NBR-SBR rubbers with suitable properties. With the possibility of specifying the required thickness (1 - 15 mm), width (1,200 - 1,400 mm) and number of inserts (0 - 2 pcs). Click and choose. Complete the exact specification in the configurator.



### ADDITIONAL INFORMATION

Temperature range -25/+80 °C, short-term +90 °C.

### RESISTANCE

- Alkaline resistance NO
- Acid resistance NO
- Oil resistance HIGHLY RESISTANT
- Gasoline resistance MEDIUM RESISTANT

### CONFIGURATION OPTIONS

#### THICKNESS

1 mm	(+/- 0,2 mm)
1.5 mm	(+/- 0,2 mm)
2 mm	(+/- 0,2 mm)
3 mm	(+/- 0,3 mm)
4 mm	(+/- 0,4 mm)
5 mm	(+/- 0,5 mm)
6 mm	(+/- 0,5 mm)
8 mm	(+/- 0,6 mm)
10 mm	(+/- 0,6 mm)
12 mm	(+/- 1,0 mm)
15 mm	(+/- 1,0 mm)

#### WIDTH

1200 mm	(+/- 10 mm)
1400 mm	(+/- 10 mm)

#### LENGTH

20 m	(+/- 200 mm)
10 m	(+/- 200 mm)
5 m	(+/- 200 mm)

#### NUMBER OF REINFORCEMENT LAYERS

without reinforcement layers	(for thicknesses 1 - 15 mm)
.....	
1 reinforcement layer	(for thicknesses 2 - 15 mm)
2 reinforcement layers	(for thicknesses 3 - 15 mm)

# RUBBER SHEETING OIL RESISTANT 7645 — NBR-SBR

7645 SWELLING RATES

