

# RUBBER SHEETING FOR MECHANICAL STRESS 7749 — SBR



70 +/- 5	Sh A	10	MPa	1,19	g/cm <sup>3</sup>	300	%	-25 - +80	°C	1-15	mm	INTERIOR
HARDNESS		TENSILE STRENGTH		DENSITY		ELONGATION		TEMPERATURE RANGE		THICKNESS		ENVIRONMENT

Sealing plate for general use with the added property of increased tensile strength. Suitable for environments without special requirements for resistance to negative influences. Made on the basis of SBR rubber compound with various chemical and physical-mechanical properties. With the possibility of specifying the required thickness (1 - 15 mm), width (1,200 - 1,400 mm) and number of inserts (0 - 2 pcs).



## RESISTANCE

Weather resistance	NO
Ozone resistance	NO
UV resistance	NO
Alkaline resistance	MEDIUM RESISTANT
Acid resistance	MEDIUM RESISTANT
Oil resistance	NO
Gasoline resistance	NO

## CONFIGURATION OPTIONS

### THICKNESS

1 mm	(+/- 0,2 mm)
1.5 mm	(+/- 0,2 mm)
2 mm	(+/- 0,2 mm)
3 mm	(+/- 0,3 mm)
4 mm	(+/- 0,4 mm)
5 mm	(+/- 0,5 mm)
6 mm	(+/- 0,5 mm)
8 mm	(+/- 0,6 mm)
10 mm	(+/- 0,6 mm)
12 mm	(+/- 1,0 mm)
15 mm	(+/- 1,0 mm)

### WIDTH

1200 mm	(+/- 10 mm)
1400 mm	(+/- 10 mm)

### LENGTH

20 m	(+/- 200 mm)
10 m	(+/- 200 mm)
5 m	(+/- 200 mm)

### NUMBER OF REINFORCEMENT LAYERS

without reinforcement	(for thicknesses 1 - 15 mm)
.....	
1 reinforcement layer	(for thicknesses 2 - 15 mm)
.....	
2 reinforcement layers	(for thicknesses 3 - 15 mm)