

RUBBER SHEETING SOUNDPROOF 9001 — CR-NR



65 +/- 5	Sh A	3	MPa	2,44	g/cm ³	100	%	-25 - +80	°C	2.5	mm	INTERIOR
HARDNESS		TENSILE STRENGTH		DENSITY		ELONGATION		TEMPERATURE RANGE		THICKNESS		ENVIRONMENT

Sealing plate made of a special self-extinguishing material with acoustic properties of a sound barrier. Designed for use without demands for resistance to negative environmental influences and without mechanical stress. Made on the basis of CR and NR rubbers with slight resistance to acids, alkalis and oils. In standard thickness 2.5 mm and width max 1,400 mm. Complete the exact specification in the configurator.



RESISTANCE

Alkaline resistance MEDIUM RESISTANT
 Acid resistance MEDIUM RESISTANT
 Oil resistance MEDIUM RESISTANT

CONFIGURATION OPTIONS

THICKNESS
 2.5 mm (+/- 0,3 mm)

WIDTH
 1200 mm (+/- 10 mm)

LENGTH
 10 m (+/- 200 mm)

NUMBER OF REINFORCEMENT LAYERS
 without reinforcement (for thicknesses 2.5 mm layers)

RUBBER SHEETING SOUNDPROOF 9001 —
CR-NR

SOUND LOSS TM E-90

